



4444 Hunt St. Pryor, OK 74361  
Email: info@gaproofing.us  
Phone: 918-825-5200  
Fax: 918-825-5207

Company Website: [GAProofing.us](http://GAProofing.us)  
Dealer Support: [GAPdealers.com](http://GAPdealers.com)

# 15 ASTM 4869 FELT



## WE OWN THE PAPER MILL

LOWER PRICING.  
LOWER LEAD TIMES.  
HIGHER QUALITY RAW MATERIALS.

# 15 ASTM 4869 FELT

## PRODUCT DESCRIPTION

GAP 15 roofing felt is a widely accepted underlayment product that is manufactured from organic felt and is saturated with asphalt

## PRODUCT USE

GAP No.15 is underlayment is applied over the roofing deck before installation of asphalt shingles. This is recommended for use with 20 and 25 year asphalt shingles.

## TECHNICAL DATA

ASTM D 4869 Type 1

|  |                     |
|--|---------------------|
|  | 36"                 |
| Width of Roll                              | 432 sq ft           |
| Roof Coverage per Roll                     | 8.0 lbs/ 100 ft sq  |
| Mass of Saturated Felt Roll                | 4.0 lbs / 100 ft sq |
| Mass of Asphalt Saturant                   | 4.0 lbs / 100 ft sq |
| Mass of Desaturated Felt                   | 100%                |
| Saturation by Weight (min)                 | 75%                 |
| Saturation Efficiency (min) by Weight      |                     |
| Breaking Strength at 77F (min)             | 30 lbf/in           |
| Machine Direction                          | 15 lbf/in           |
| Cross Direction                            | YES                 |
| Pass 4 Hour Liquid Transmission Water Test | 1/2" radius         |

Pallet Size 42" X 42" No. of Rolls per Pallet = 30 for 4 Square Rolls

**Note:**  
GAP # 15 is available in 2, 3, 4  
Square Rolls and 400 Sq. ft Roll

## MANUFACTURING LOCATIONS:

Pryor, OK

McGregor, TX

Shafter, CA

Jasper, FL