



4444 Hunt St. Pryor, OK 74361  
Email: info@gaproofing.us  
Phone: 918-825-5200  
Fax: 918-825-5207

Company Website: [GAProofing.us](http://GAProofing.us)  
Dealer Support: [GAPdealers.com](http://GAPdealers.com)

# ASTM 15 D226 FELT



## WE OWN THE PAPER MILL

LOWER PRICING.  
LOWER LEAD TIMES.  
HIGHER QUALITY RAW MATERIALS.

## ASTM 15 D226 FELT

### PRODUCT DESCRIPTION

GAP ASTM 15 D226 is an underlayment product that is manufactured from superior quality organic felt that is saturated with asphalt

### PRODUCT USE

GAP ASTM 15 D 226 is an underlayment that is applied over the roofing deck before installation of asphalt shingles.

### TECHNICAL DATA

ASTM D 226 Type 1

Width of Roll	36"
Roof Coverage per Roll	432 sq ft
Mass of Saturated Felt Roll	11.5 lbs/ 100 ft sq
Mass of Asphalt Saturant	6.2 lbs / 100 ft sq
Mass of Desaturated Felt	5.2 lbs / 100 ft sq
Saturation by Weight (min)	10%
Average (min) Breaking Strength	
Machine Direction (with fiber grain)	30 lbf/in
Across fiber grain	15 lbf/in
Pliability at 77F when bend 90 degrees	1/2" radius
Max. loss on heating at 221F	4%

Pallet Size 42" X 48" No. of Rolls per Pallet = 25

### MANUFACTURING LOCATIONS:

Pryor, OK

McGregor, TX

Shafter, CA

Jasper, FL